

Light Reflectance & Total Solar Absorption Values

Colour	Light Reflectance Values ¹	Total Solar Absorption ²
Satin Finish		
Windsor Grey	6.7	93.8
Karaka	6.7	93.9
Permanent Green	9.2	88.4
Ironsand	6.7	93.6
Terracotta	20.3	69.3
Anvil	8.26	92.4
Beige	31.6	70.6
Ebony	4.6	95.5
New Denim Blue	9.8	91.3
Sandstone Grey	26.8	78.6
Scoria	8.6	87.4
Grey Friars	9.1	92.3
Thunder Grey	11.7	89.3
Drover Grey	38.6	66.7
Titania	65.5	42.2
Flax	5.6	94.6
Gull Grey	47.6	58.5
Tidal Grey	12.9	88.6
Alpine Stone	66.9	39.3
Textured Finish		
Ashwood	16.2	84.9
Cedar	5.8	89.3
Charcoal	3.5	96.7
Teak	5.1	92.8
Onyx	9.9	89.3
Pepper	7.9	90.4
Autumn	5.8	87.7
Midnight	2.2	95.0
Rainforest	4.4	95.4
Eclipse	3.5	96.7

1. ASTM Reference C609-7. Instrument: Macbeth Color-Eye 7000A

2. ASTM Reference C1549 & E903-96. Instrument: Devices & Device Reflectometer, Model SSE-ER