

Light Reflectance & Total Solar Absorption Values

Colour	Light Reflectance Values ¹	Total Solar Absorption ²	Gloss Level ³
Satin Finish			
Windsor Grey	6.7	93.8	<7%
Karaka	6.7	93.9	<7%
Permanent Green	9.2	88.4	<7%
Ironsand	6.7	93.6	<7%
Terracotta	20.3	69.3	<7%
Beige	31.6	70.6	<7%
Ebony	4.6	95.5	<7%
New Denim Blue	9.8	91.3	<7%
Sandstone Grey	26.8	78.6	<7%
Scoria	8.6	87.4	<7%
Grey Friars	9.1	92.3	<7%
Thunder Grey	11.7	89.3	<7%
Titania	65.5	42.2	<7%
Flax	5.6	94.6	<7%
Gull Grey	47.6	58.5	<7%
Textured Finish			
Ashwood	16.2	84.9	<2%
Cedar	5.8	89.3	<2%
Charcoal	3.5	96.7	<2%
Teak	5.1	92.8	<2%
Onyx	9.9	89.3	<2%
Pepper	7.9	90.4	<2%
Autumn	5.8	87.7	<2%
Midnight	2.2	95.0	<2%
Eclipse	3.5	96.7	<2%
Charcoal Blend	3.5	-	<2%
Barkwood	4.8	-	<2%
Weathered Wood	5.3	-	<2%
Walnut	6.5	90.2	<2%

1. ASTM Reference C609-7. Instrument: Macbeth Color-Eye 7000A

2. ASTM Reference C1549 & E903-96. Instrument: Devices & Device Reflectometer, Model SSE-ER

3. ASTM Reference D523-11:2018. Gloss level measured at 60°